



QDRAIN C15 65 12F

Year of last update: **2024**



Function: **Drainage**

STRUCTURE: drainage geocomposite made by a 3-dimensional, high void ratio monofilaments core heat bonded with two filter geotextiles

FILTER GEOTEXTILES

				<i>tol</i>
Raw material			PP	
Weight	EN ISO 9864	g/m ²	120	+/-12
Thickness	EN ISO 9863-1	mm	0,8	±20%
Tensile strength MD/CMD	EN ISO 10319	kN/m	9/9	-1,5/-1,5
Elongation at max load MD/CMD	EN ISO 10319	%	55/60	±25
CBR puncture resistance	EN ISO 12236	N	1400	-140
Cone drop test	EN ISO 13433	mm	33	+6
Water permeability normal to the plane	EN ISO 11058	mm/s	85	-30
Opening size	EN ISO 12956	micron	90	±30

DRAINAGE CORE

				<i>tol</i>
Raw material			PP	
Weight	EN ISO 9864	g/m ²	650	+/-10%
Width		m	2-4	+/-3%

GEOCOMPOSITE

				<i>tol</i>
Weight	EN ISO 9864	g/m ²	890	+/-10%
Thickness	EN ISO 9863-1	mm	15	±2
Tensile strength MD/CMD	EN ISO 10319	kN/m	18/18	+/-2
Elongation at max load MD/CMD	EN ISO 10319	%	80/80	±35

HYDRAULIC PERFORMANCES

Plane flow capacity MD	EN ISO 12958-1		l/(m·s)			<i>±25 %</i>
	Hydraulic gradient	Contact	<i>i = 0,04</i>	<i>i = 0,10</i>	<i>i = 1</i>	
	Load: 20 kPa	S/R	0,64	1,06	3,80	
	" 50 kPa	S/R	0,25	0,43	1,80	
	" 100 kPa	S/R	0,05	0,10	0,40	

S/S: Soft/Soft Contact - S/R: Soft/Rigid Contact - R/R: Rigid/Rigid Contact

STANDARD DIMENSIONS

				<i>tol</i>
Width		m	2-4	±3%
Length		m	25	±2%

To be covered within one month after installation



The information given in this data sheet is to the best of our knowledge true and correct. TeMa srl reserves the right to change its product specifications at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.

TeMa Technologies and Materials srl

Via dell'Industria 21 - 31029 Vittorio V.to (TV) Tel. +39.0438.50.31 - Fax +39.0438.50.34.60 - e-mail: info@temacorporation.com - www.temacorporation.com

REV. 1/2024