



# QDRAIN ZW5 40 10F

Year of last update: **2024**



Function: **Drainage**

**STRUCTURE:** drainage geocomposite made by a 3-dimensional, high void ratio monofilaments core heat bonded with two filter geotextiles

## FILTER GEOTEXTILES

|  |               |                  |              | <i>tol</i> |
|--|---------------|------------------|--------------|------------|
| Raw material                           |               |                  | <b>PP</b>    |            |
| Weight                                 | EN ISO 9864   | g/m <sup>2</sup> | <b>100</b>   | -10%       |
| Thickness                              | EN ISO 9863-1 | mm               | <b>0,65</b>  | ±20%       |
| Tensile strength MD/CMD                | EN ISO 10319  | kN/m             | <b>6/6</b>   | -1/-1      |
| Elongation at max load MD/CMD          | EN ISO 10319  | %                | <b>45/65</b> | ±20        |
| CBR puncture resistance                | EN ISO 12236  | N                | <b>1000</b>  | -100       |
| Cone drop test                         | EN ISO 13433  | mm               | <b>34</b>    | 9          |
| Water permeability normal to the plane | EN ISO 11058  | mm/s             | <b>90</b>    | -40        |
| Opening size                           | EN ISO 12956  | micron           | <b>95</b>    | ±35        |

## DRAINAGE CORE

|              |             |                  |            | <i>tol</i> |
|--------------|-------------|------------------|------------|------------|
| Raw material |             |                  | <b>PP</b>  |            |
| Weight       | EN ISO 9864 | g/m <sup>2</sup> | <b>400</b> | +/-10%     |
| Width        |             | m                | <b>2-4</b> | +/-3%      |

## GEOCOMPOSITE

|                               |               |                  |              | <i>tol</i> |
|-------------------------------|---------------|------------------|--------------|------------|
| Weight                        | EN ISO 9864   | g/m <sup>2</sup> | <b>600</b>   | ±10%       |
| Thickness                     | EN ISO 9863-1 | mm               | <b>5,5</b>   | ±1         |
| Tensile strength MD/CMD       | EN ISO 10319  | kN/m             | <b>12/12</b> | -2/-2      |
| Elongation at max load MD/CMD | EN ISO 10319  | %                | <b>80/80</b> | +/-35      |

## HYDRAULIC PERFORMANCES

| Plane flow capacity MD | EN ISO 12958-1            |                | l/(m·s)         |                 |              | <i>±25 %</i> |
|------------------------|---------------------------|----------------|-----------------|-----------------|--------------|--------------|
|                        | <i>Hydraulic gradient</i> | <i>Contact</i> | <i>i = 0,04</i> | <i>i = 0,10</i> | <i>i = 1</i> |              |
|                        | Load: 20 kPa              | S/R            | 0,12            | 0,20            | 0,90         |              |
|                        | " 50 kPa                  | S/R            | 0,10            | 0,15            | 0,70         |              |
|                        | " 100 kPa                 | S/R            | 0,05            | 0,07            | 0,35         |              |

S/S: Soft/Soft Contact - S/R: Soft/Rigid Contact - R/R: Rigid/Rigid Contact

## STANDARD DIMENSIONS

|        |  |   |            | <i>tol</i> |
|--------|--|---|------------|------------|
| Width  |  | m | <b>2-4</b> | ±3%        |
| Length |  | m | <b>50</b>  | ±2%        |

To be covered within one month after installation



The information given in this data sheet is to the best of our knowledge true and correct. TeMa srl reserves the right to change its product specifications at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.

TeMa Technologies and Materials srl

Via dell'Industria 21 - 31029 Vittorio V.to (TV) Tel. +39.0438.50.31 - Fax +39.0438.50.34.60 - e-mail: info@temacorporation.com - www.temacorporation.com

REV. 1/2024