



XGrid PET-C-0 200/20

Reference norms: **EN 13249, EN 13250, EN 13251, EN 13253, EN 13254, EN 13255, EN 13257, EN 13265**

Certificate number: **1213 - CPR - 5326**

Application: **Reinforcement**



STRUCTURE: Knitted grid from high-tenacity multifilament polyester yarns with black polymeric coating which can provide best resistance of UV and durability

PROPERTIES OF RAW MATERIAL

Raw material	PET	<i>tol</i>
Coating	polymeric	

MECHANICAL PROPERTIES

Strength resistance MD - T _{ULT}	EN ISO 10319	kN/m	≥ 200	
Elongation at max load MD	EN ISO 10319	%	10	+/-2,5
Strength resistance CMD	EN ISO 10319	kN/m	≥ 20	
Elongation at max load CMD	EN ISO 10319	%	11	+/-2,5
Long term design strength MD - T _{AL} (*)	FHWA NHI-00-043	kN/m	110,57	

(120 years life, 20°, 5<pH<8, sand)

CHEMICAL PROPERTIES OF RAW MATERIAL

Carboxyl End Group - CEG	GRI GG7	mmol/kg	16,6	<i>tol</i>
Molecular weight	GRI GG8	Mn	40.000	

TYPICAL DIMENSIONS

Mesh dimensions MD/CMD	mm	25x29	<i>tol</i>
Roll width	m	4,15 - 5,25	+/-0,1
Roll length	m	100	+/-0,5

MD: Machine direction - longitudinal direction

CMD: Cross machine direction - transverse direction



The information given in this data sheet is to the best of our knowledge true and correct. TeMa srl reserves the right to change its product specifications at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.

TeMa Technologies and Materials srl

Via dell'Industria 21 - 31029 Vittorio V.to (TV) Tel. +39.0438.50.31 - Fax +39.0438.50.34.60 - e-mail: info@temacorporation.com - www.temacorporation.com

rev.1 2023